

## **TEST REPORT**

DATE: 03-04-2019	Page 1 of 1	<b>TEST NUMBER</b> : 0254590
CLIENT	Faetgepper a/s	

TEST METHOD CONDUCTED	AATCC 16 Colorfastness to Light (Option 3)	
-----------------------	--	--



	DESCRIPTION OF TEST SAMPLE
IDENTIFICATION	Highline 630
BACKING	Woven Synthetic

## **GENERAL PRINCIPLE**

This test specimen is exposed to a predetermined amount of radiant energy under specified conditions of temperature and relative humidity. The lightfastness of the specimen is assessed by comparing the exposed and the unexposed portions of the test sample with the AATCC Gray Scale for Evaluating Color Change.

## **TEST RESULTS**

EXPOSURE	40 AFU
EXPOSURE	40 AI 0

COLOR	RATING	IDENTIFICATION	RATING
Highline 630	4.0		

IDENTIFICATION	RATING

	AATCC RATING KEY
5	No change
4	Slight change
3	Noticeable change
2	Considerable change
1	Severe change

APPROVED BY: Lary aslewry



This facility is accredited by the National Voluntary Laboratory Accreditation Program for the specific scope of accreditation under Lab Code 100297. This accreditation does not constitute an endorsement, certification, or approval by NIST or any agency of the United States Government for the producttested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory, Inc., shall not be used under any circumstance in advertising to the general public.



AP LAB CODE 100297-0