

ege testcertificate

Subject:	Light Reflectance
Reference No.:	1316
Reference:	Highline 1400 80/20
Description of sample:	Tuftet carpet, cut pile Colour palettes 5500 Colour Scale 1-12 5520 Colour Scale 1-12 5575 Colour Scale 1-12 5595 Colour Scale 1-12
Testing atmosphere	Unless otherwise specified the sample has been conditioned and tested, where appropriate, in the standard atmosphere for conditioning and testing textiles EN ISO 139:2005 of 65 ± 4 % R.H. and 20 ± 2 °C.

Background

LRV is an instrumental measurement made using a spectrophotometer.

It is equivalent to CIE Y and is the proportion of visible light reflected by a surface, weighted for the sensitivity to light of the human eye.

LRV is expressed on a scale of 0-100 where absolute white has a value of 100 and absolute black has a value of 0. In practice white may be about 85 and black about 6.

For people with adequate vision, difference in hue or chroma (colour intensity), provide sufficient visual contrast. But for people who are visually impaired the main feature of a surface which determines the ability to identify differences in colour is the amount of light the surface reflects, or it's LRV.

Test procedure

The light reflectance value for the sample was determined using a Chroma Meter reflectance spectrophotometer with a large area CR-410 measuring head.

The sample was subjected to measurements and viewed at 0° with illuminant C. The light reflectance was determined using CIE Y, according to BS 8493:2008.

ege[®]

we create more than carpets

egetæpper a/s
Industrivej Nord 25
Postbox 190
DK-7400 Herning

Tel: +45 97 11 88 11
Fax: +45 97 11 95 80

ege@ege.dk
www.egecarpet.com

CVR 38 45 42 18

Test results CIE Y :

Colour no.	Colour palette 5500	Colour no.	Colour palette 5520	Colour no.	Colour palette 5575	Colour no.	Colour palette 5595
gb1 - K40501	11,99	gb1 - A20041	50,43	gb1 - K28328	36,28	gb1 - K28601	24,66
gb2 - K40502	2,54	gb2 - A20042	30,95	gb2 - K28329	22,79	gb2 - K28602	15,33
gb3 - K40503	9,08	gb3 - A20043	15,61	gb3 - K28378	16,44	gb3 - K28603	6,48
gb4 - K40504	36,02	gb4 - K20044	7,70	gb4 - K28374	6,49	gb4 - K20012	2,27
gb5 - K40505	3,51	gb5 - K20045	3,61	gb5 - K28366	2,92	gb5 - H28605	2,10
gb6 - K40506	3,88	gb6 - K20046	10,11	gb6 - K28364	5,01	gb6 - K28606	3,60
gb7 - K40507	3,36	gb7 - K20047	4,41	gb7 - K28380	14,35	gb7 - K28607	3,82
gb8 - K40508	9,0	gb8 - K20048	16,42	gb8 - K28379	21,51	gb8 - K28608	13,88
gb9 - K40509	4,58	gb9 - K20049	5,24	gb9 - K27886	15,73	gb9 - K28609	18,80
gb10 - K40510	11,67	gb10 - K20050	5,20	gb10 - K28360	17,27	gb10 - K28610	8,82
gb11 - K40511	4,40	gb11 - K20051	2,70	gb11 - K28367	5,94	gb11 - H28611	3,17
gb12 - K40512	14,43	gb12 - K20012	2,00	gb12 - K28368	2,45	gb12 - H28632	2,59

The information contained on page no 1-2 of this certificate is hereby certified to be correct statement of the tests and investigations carried out by ege testlaboratory on the material referred to.

Signed by



Dorthe Daa Pedersen
Laboratory Technician

Reported By



Henrik Schmidt Hansen
Group CSR Director