

## **TEST REPORT**

**CLIENT** Egetaepper a/s

TEST METHOD CONDUCTED

ASTM D5252 Standard Practice for the Operation of the

Hexapod Tumble Drum Tester



DESCRIPTION OF TEST SAMPLE		
IDENTIFICATION	Highline Loop ECT350	
CONSTRUCTION	Multi-Level Loop Pile	
BACKING	Attached Cushion	
REFERENCE	Rawline Scala	

#### **GENERAL PRINCIPLE**

The test specimen is subjected to "Hexapod" tumbling in 2,000 cycle increments. A CRI/SOA upright vacuum was used to make four forward and backward passes along the length of the specimen after each 2,000 cycles.

After the specified total number of cycles is completed, the test specimen is visually assessed by three technicians for appearance change in accordance with the ASTM D7330 "Test Method for Assessment of Surface Appearance Change in Pile Floor Coverings Using Standard Reference Scales".

### **TEST RESULTS**

## LIGHT BALL

NUMBER OF CYCLES	APPEARANCE RATING	COLOR CHANGE RATING*
12,000	4.5	4.0

\*NOTE: At the client's request, an additional rating was reported which assessed perceived color change in the test specimen resulting from pile distortion. The color change rating was done in accordance with AATCC Evaluation Procedure 1, using the Gray Scale for Color Change.

# APPEARANCE RATING KEY

- **5** Excellent: No visual change noticeable
- 4 Good: Slight change due to disturbance of pile
- **3** Fair: Noticeable change due to pile disturbance or matting
- 2 | Poor: Loss of texture due to pile disturbance and/or matting
- 1 Very Poor: Severe pile disturbance and/or matting

#### **COLOR CHANGE RATING KEY**

- 5 Negligible or no change
- 4 Slight change
- 3 | Moderate change
- 2 Considerable change
- Severe change

APPROVED BY:

Lang aslung



This facility is accredited by the National Voluntary Laboratory Program for the specific scope of accreditation under lab code 100297-0. This accreditation does not constitute endorsement, certification, or approval by NIST or any agency of the United States Government for the product tested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.

714 Glenwood Place Dalton, GA 30721 Phone: 706-226-3283 Fax: 706-226-6787 email: protest@optlink.us



APPROVED BY:



This facility is accredited by the National Voluntary Laboratory Program for the specific scope of accreditation under lab code 100297-0. This accreditation does not constitute endorsement, certification, or approval by NIST or any agency of the United States Government for the product tested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.

Lang aslung

714 Glenwood Place Dalton, GA 30721 Phone: 706-226-3283 Fax: 706-226-6787 email: protest@optlink.us